



CENTRO SERVIZI TESSILI s.r.l.
Laboratorio analisi chimiche e prove fisiche
TEXDECOR CASAMANCE

FABRIC TEST
Lab. ref. N° 26312

Date received: 14/04/22
 Date issued: 19/04/22
 Article: FLORA
 Col.:

PHYSICAL TESTS	RESULT	TESTING METHODS
Ignitability of upholstery composites Ignition source 1 : butane	1st flame application: On contact with the butane flame the cover material melt and ignite. The sample ignite after removal of the flame and burn for 6 sec. Smoke duration and or smouldering 7 sec. Extent of damage to component : <u>Horizontal</u> : Width : 82 mm , Length: 26 mm <u>Vertical</u> : Width : 84 mm , Length: 103 mm Result : sample Pass the test. Not Ignition	BS 5852 Schedule 5 part 1 <i>Identification and construction of test specimens : CMHR d=24-26 Kg/m³ in a seat/back configuration and covered by the fabric to be tested.</i> <i>Time of ignition : 20 sec.</i> <i>Conditioning of material : 48hr - 20°C - 65% r.h.</i>

Tecnico di laboratorio
 Cristiano Benigni

Responsabile di laboratorio
 Dott. Simone Calamai



Via 5 giornate di Milano n°24
 Tel. +39 0574 622887 fax +39 0574 1660601

59100 PRATO
 e-mail: centroservizitessili@libero.it